

Corro-Coat FC 2100 Fast Epoxy TECHNICAL DATA

SOLVENT-FREE EPOXY COATING SYSTEM

Mix and Match Corro-Coat FC 2100 Bases and Curing Agents

<p>Protective Coating Top Coat Corrosion Protection Apply/Cures Underwater</p>	<p>Solvent-Free High Build Non-Sag Formulation Excellent Chemical and Abrasion Resistance Easy 2:1 Mixing Ratio Feldspar Ceramic and Kevlar™ Reinforced</p>
--	---

STANDARD PRODUCT DESCRIPTION	<p>Corro Coat FC 2100 Fast is a 100% solids, next generation, epoxy coating featuring excellent chemical and abrasion resistance, high build tile like glaze finish that will withstand severe abuse. Can be applied to surfaces above and below the water line and is suitable for use in temperatures from 65°F down to 38°F. Corro Coat FC 2100 Fast bonds to cold concrete (wet and dry), fiberglass, steel and wood surfaces. Novalac and thicker (nonhazmat) versions available. High temperature (hazmat) version is also available.</p>
USES	<p>Excellent for use in temperatures as low as 38°F. Most corrosive environments Marine, chemical, pulp and paper Spillways, piping, pilings, columns Excellent as a finish top coat</p>
FEATURES	<p>Solvent-Free High Gloss Convenient 2 to 1 ratio by volume Non-blushing and non-water spotting Non-corrosive and Non-hazmat Kevlar™ microfibers reinforce against hairline cracking and chipping Feldspar (ceramic plates/needles) provides extreme abrasive resistance</p>
VISCOSITY	<p>Viscosity at 72°F: Part A: 25,000 cps Part B: 100 cps Mixed: 1,000 cps</p>
PHYSICAL PROPERTIES	<p>COLOR Light gray, other colors in 15 gallon units COMPRESSIVE STRENGTH ASTM D695 12,000 psi TENSILE STRENGTH ASTM D638 5,500 psi ELONGATION AT BREAK 30 % ABRASION RESISTANCE CS-17 WHEEL, 1 kg LOAD ASTM D4060 0.14 gm loss WATER ABSORPTION ASTM D570 0.09 % (2 hour boil) FLEXURAL STRENGTH ASTM D790 6,900 psi SHORE D HARDNESS ASTM D2240 89-90 HEAT DISTORTION ASTM D649 140° F TEMPERATURE BOND STRENGTH TO: Concrete 100 % concrete failure FILM THICKNESS 10-35 mils (average: 100 sq. ft./gallon @ 16 mils)</p>

MULTI-VENDOR EPOXY SOLUTIONS

Corro Coat FC 2100 Fast Epoxy TECHNICAL DATA

CURE SCHEDULE	POT LIFE @ 55°F approx. 45 minutes FULL CURE @ 55°F 8 hours																																																																
CHEMICAL RESISTANCE (splash & spill)	<table style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left;">REAGENT ACIDS</th> <th style="text-align: left;">RATING</th> <th style="text-align: left;">REAGENT ALKALIES</th> <th style="text-align: left;">RATING</th> </tr> </thead> <tbody> <tr> <td>Acetic 1-20%</td> <td>excellent</td> <td>Ammonium Hydroxide All</td> <td>excellent</td> </tr> <tr> <td>Chromic 1-10%</td> <td>excellent</td> <td>Calcium Chloride All</td> <td>excellent</td> </tr> <tr> <td>Citric All</td> <td>excellent</td> <td>Calcium Hypochlorite 1-15%</td> <td>excellent</td> </tr> <tr> <td>Hydrochloric All</td> <td>excellent</td> <td>Caustic Soda</td> <td>excellent</td> </tr> <tr> <td>Lactic 1-50%</td> <td>excellent</td> <td>Caustic Potash</td> <td>excellent</td> </tr> <tr> <td>Nitric 1-20%</td> <td>excellent</td> <td>Sodium Hydroxide All</td> <td>excellent</td> </tr> <tr> <td>Oxalic 1-20%</td> <td>excellent</td> <td>Sodium Sulfide 1-30%</td> <td>excellent</td> </tr> <tr> <td>Phosphoric All</td> <td>excellent</td> <td>Skydrol® Fluids</td> <td>excellent</td> </tr> <tr> <td>Sulfuric All</td> <td>excellent</td> <td>Butyl Cellosolve</td> <td>excellent</td> </tr> <tr> <td>Bleach</td> <td>excellent</td> <td>Gasoline</td> <td>excellent</td> </tr> <tr> <td>Ethanol</td> <td>excellent</td> <td>Methanol</td> <td>excellent</td> </tr> <tr> <td>Jet fuels (JP-4-6)</td> <td>excellent</td> <td>Toluene</td> <td>excellent</td> </tr> <tr> <td>Methyl Ethyl Keytone</td> <td>excellent</td> <td>Xylene</td> <td>excellent</td> </tr> <tr> <td>Trichloroethane</td> <td>excellent</td> <td>Sewerage (gas & solids)</td> <td>excellent</td> </tr> <tr> <td>Water All</td> <td>excellent</td> <td></td> <td></td> </tr> </tbody> </table>	REAGENT ACIDS	RATING	REAGENT ALKALIES	RATING	Acetic 1-20%	excellent	Ammonium Hydroxide All	excellent	Chromic 1-10%	excellent	Calcium Chloride All	excellent	Citric All	excellent	Calcium Hypochlorite 1-15%	excellent	Hydrochloric All	excellent	Caustic Soda	excellent	Lactic 1-50%	excellent	Caustic Potash	excellent	Nitric 1-20%	excellent	Sodium Hydroxide All	excellent	Oxalic 1-20%	excellent	Sodium Sulfide 1-30%	excellent	Phosphoric All	excellent	Skydrol® Fluids	excellent	Sulfuric All	excellent	Butyl Cellosolve	excellent	Bleach	excellent	Gasoline	excellent	Ethanol	excellent	Methanol	excellent	Jet fuels (JP-4-6)	excellent	Toluene	excellent	Methyl Ethyl Keytone	excellent	Xylene	excellent	Trichloroethane	excellent	Sewerage (gas & solids)	excellent	Water All	excellent		
REAGENT ACIDS	RATING	REAGENT ALKALIES	RATING																																																														
Acetic 1-20%	excellent	Ammonium Hydroxide All	excellent																																																														
Chromic 1-10%	excellent	Calcium Chloride All	excellent																																																														
Citric All	excellent	Calcium Hypochlorite 1-15%	excellent																																																														
Hydrochloric All	excellent	Caustic Soda	excellent																																																														
Lactic 1-50%	excellent	Caustic Potash	excellent																																																														
Nitric 1-20%	excellent	Sodium Hydroxide All	excellent																																																														
Oxalic 1-20%	excellent	Sodium Sulfide 1-30%	excellent																																																														
Phosphoric All	excellent	Skydrol® Fluids	excellent																																																														
Sulfuric All	excellent	Butyl Cellosolve	excellent																																																														
Bleach	excellent	Gasoline	excellent																																																														
Ethanol	excellent	Methanol	excellent																																																														
Jet fuels (JP-4-6)	excellent	Toluene	excellent																																																														
Methyl Ethyl Keytone	excellent	Xylene	excellent																																																														
Trichloroethane	excellent	Sewerage (gas & solids)	excellent																																																														
Water All	excellent																																																																
APPLICATION	<p>Surface to be topcoated must be clean and free of oils, grease and loose contamination. Mix Corro Coat FC 2100 Fast epoxy base with the Corro Coat FC 2100 Fast curing agent. Use a mechanical mixer if possible to ensure thorough mixing. The mixing ratio is 2/1 (base/curing agent) by volume. Corro Coat FC 2100 Fast does not require a 'sweat-in' or induction time and the mixed components should be used immediately.</p> <p>Potlife is approximately 45 minutes at 55°F, so mix only the amount of epoxy that can be easily applied within that time limit. Apply using a brush, roller (product is at the upper limits of rollability), or squeegee. This product can be thinned for improved rollability or thickened to paste like viscosity.</p>																																																																
TEMPERATURE	Corro Coat-FC2100 Fast may be applied in temperatures between 65°F and 38° F.																																																																
TRANSPORT	Corro-Coat FC2100 Fast is hazardous for shipping: UN2735, Packing Group III, Class 8, Corrosive.																																																																

SAFETY: This is a hazardous material if misused. Read and understand the Material Safety Data Sheet (MSDS) before use.

WARRANTY DISCLAIMER: The technical data given herein has been compiled for your help and guidance and is based upon our experience and knowledge. However, as we have no control over the use to which this information is put, no warranty, express or implied is intended or given except that these goods shall be of merchantable quality and buyer assumes all risk and liability for results obtained by the use of the materials covered in this data sheet, whether used singly or in combination with other products. We assume no responsibility whatsoever for coverage, performance or damages, including injuries resulting from use of this information or of products recommended herein. The sale and use of this product is governed by Progressive Products, Inc.'s Warranty Disclaimer and Return Policy.

Manufactured by: ERC in RI	Distributed by: Progressive Epoxy Polymers, Inc. 48 Wildwood Dr. Pittsfield, NH 03263-3406	Tel: 603-435-7199 Fax: 603-435-7182 www.epoxyproducts.com info@epoxyproducts.com
-------------------------------	---	---