

Bio-Clear 810[®] Epoxy TECHNICAL DATA

Pourable Table Top Coating - Solvent-Free Epoxy Coating

Part of the Epoxy/Copper System

Cycloaliphatic
Crystal Clear
Slow, Gentle Cure
Cures to Wet or Damp Surfaces

Solvent-Free
Easy 2:1 Mixing Ratio (1:.43 by weight)
Approx. 20% Elongation

<p>STANDARD PRODUCT DESCRIPTION</p>	<p>Bio-Clear 810 Epoxy is a 100% solids, low viscosity, clear resin system designed for many applications including damp and wet surfaces. This product is moisture insensitive and has good chemical resistance and physical properties including approximately 20% elongation, slow and gentle exotherm and has a cycloaliphatic curing agent. Best applied to rough surfaces or as a thick film as product will 'dimple', crawl/creep if brushed or rolled onto smooth surfaces.</p>
<p>USES</p>	<p>Sealing Concrete Clear Coat Surface</p> <p>Table Tops Yacht Core Repair</p>
<p>FEATURES</p>	<p>Low viscosity Convenient 2 to 1 ratio by volume (1 to .43 by weight) Bonds to damp concrete Self-leveling Solvent-free (no odor)</p>
<p>CURE SCHEDULE</p>	<p>POT LIFE @ 70°F 45 minutes (6 ounce sample) larger amounts will have less time TACK FREE 8 -12 hours HARD TO TOUCH 24 hours FULLY CURED 5 days</p>
<p>DIRECTIONS</p>	<p>Surface to be topcoated must be clean and free of oils, grease and loose contamination. The epoxy and the surface to be coated should be at a constant 68 degrees or warmer for 24 hours before and after the pour. Do not apply in direct sunlight. Epoxy and application surface should be approximately the same temperature prior to application. This will minimize any effects that temperature may generate during the curing process.</p> <p>Mix Bio-Clear 810 epoxy base with the Bio-Clear 810 curing agent. Part A may have a slightly yellow tint and B should be clear prior to mixing - if not, do not proceed and contact supplier). Mixture will also be clear after mixing. A mechanical mixer will help ensure thorough mixing but if using a mechanical mixer, use a low speed to reduce the generation of air bubbles. Do not mix the epoxy in the same containers that the epoxy came in. Pour the proper ratio of the two components into a large enough container to allow adequate, vigorous mixing without having the epoxy splash out. The mixing ratio is 2/1 (base/curing agent) by volume or 1/0.43 by weight. Bubbles resulting from the mixing will rise to the surface and most or all will pop. Heat from a torch or hair drier (set on low) will usually pop most remaining bubbles. It is never possible to completely mix all of the epoxy in your mixing container. The epoxy at the corner of the bottom and sides, and on the bottom will probably not be mixed well enough. Therefore, after mixing do not try to get every last drop out of the mixing container (don't overturn the mixing container and drain it for a long period of time). Bio-Clear 810 does not require a 'sweat-in' or induction time and the mixed components should be used immediately.</p>

Bio-Clear 810[®] TECHNICAL DATA

FOR BEST RESULTS	<p>TEST the epoxy on your surface. Mix up a small amount of the epoxy (2 to 1 mix ratio) and apply to a test surface to ensure compatibility and to test your mixing method. Some surfaces will release a lot of air bubbles. Incompatible inks may bleed. Unknown or unsuspected contaminants on the surface may discolor the epoxy. Sudden changes in temperature or humidity may affect the epoxy. Make sure your raised edges or sills are leakproof and level. Once poured, it is almost impossible to stop an epoxy leak in a corner. Bio-Clear 810 cannot be brushed on. It must be poured at sufficient depth to prevent surface tension related fisheyes. A fan blowing over the freshly poured epoxy may help to reduce exotherm (heat) related problems.</p> <p>The epoxy will feel dry and hard overnight, but it takes a week for it to fully cure and harden. Do not place objects on the epoxy before then as they will stick or leave a dent or impression in the still hardening epoxy.</p> <p>Potlife is approximately 40 minutes at 75°F for a 6 ounce amount, so mix only the amount of epoxy that can be easily applied within that time limit. Apply 1/4 to 1/2 inch thick. Do not mix more than 3 gallons at a time, even on big jobs or exotherm related stress cracks may form.</p>
NOTES	<p>Unless top-coated with a UV absorber, this epoxy will yellow and eventually turn cloudy with exposure to sunlight. This epoxy will generate a considerable amount of heat when it hardens. Thin plastic containers will melt.</p> <p>Mix slowly to avoid introducing excess air bubbles. After pouring, most bubbles will come to the surface and burst. The remaining bubbles can be removed once they come to the surface with the quick pass of a heat gun.</p> <p>As noted before, test the epoxy on your surface. What happens after the clear epoxy is poured upon the surface is the sole responsibility of the purchaser. Supplier liability is limited to 1 three gallon unit maximum for Bio-Clear 810. See warranty statement.</p>
TEMPERATURE	<p>Temperature will exert a considerable influence on the rate of curing of chemically cured coatings such as Bio-Clear 810 epoxy. In broad terms expect each 10°C, (18°F), rise or fall in temperature to half or double dry times and pot lives.</p> <p>The epoxy and the surface to be coated should be at a constant 68 degrees or warmer for 24 hours before and after the pour.</p>
TRANSPORTATION	<p>Epoxy base - Nonregulated by USDOT, IATA & IMO. Curing agent - USDOT, IATA & IMO "Regulated". Class 8, Packing group III, UN 2735, Corrosive</p>

SAFETY: This is a hazardous material if misused. Read and understand the Material Safety Data Sheet (MSDS) before use.

WARRANTY DISCLAIMER: The technical data given herein has been compiled for your help and guidance and is based upon our experience and knowledge. However, as we have no control over the use to which this information is put, no warranty, express or implied is intended or given. We assume no responsibility whatsoever for coverage, performance or damages, including injuries resulting from use of this information or of products recommended herein. The sale and use of this product is governed by Progressive Products, Inc.'s Warranty Disclaimer and Return Policy.

Manufactured by:
RTC in IL

Distributed by:
Progressive Epoxy Polymers, Inc.
48 Wildwood Drive
Pittsfield, NH 03263-3406

Tel: 603-435-7199
Fax: 603-435-7182
www.epoxyproducts.com
info@epoxyproducts.com