

Aluthane™ TECHNICAL DATA

Aluminum Filled Urethane Metallic Coating

**Primer
Top Coat
Floor Coating
Protective Coating**

**Excellent Corrosion Resistance
Easy One Component Formulation
Forms a Hard Surface
VOC Class: Metallic coating VOC - 356 g/l**

<p>STANDARD PRODUCT DESCRIPTION</p>	<p>A one component, moisture cured polyurethane aluminum metallic coating. Has excellent adhesion to sound, tightly adherent rusty steel, wood, concrete and other marginal or poorly prepared surfaces. This low viscosity, high 'wetting' coating undergoes a rapid molecular weight change as it polymerizes into a high molecular weight finish which provides excellent corrosion resistance and abrasion resistance. Its resistance to creeping, undercutting, and blistering is superior to epoxy primers. Aluthane™ is also a barrier primer or tie coat to prevent lifting of strong solvent top coats over conventional coatings, and most chemical coatings. Aluthane produces a shiny silver finish on rough surfaces and a flat galvanized look on smooth surfaces.</p>
<p>USES</p>	<ul style="list-style-type: none"> ● Excellent as a universal primer for metal, steel, concrete, wood, fiberglass, plastic, clean or weathered galvanized metal. ● For use over sound, tightly adherent rust where only wire brush or hand tool cleaning is feasible. For remedial painting of fences, metal buildings, hand and guard rails, pumps, pipelines, grating, and other hard to clean surfaces. ● Ideal as a barrier coat over lead based coatings and conventional coatings. The low solvency power of Aluthane enables it to be applied over most type coatings without causing lifting. A test sample should be made to confirm adhesion. Most generic types of chemical or conventional coatings may be applied over Aluthane with excellent adhesion. ● Has excellent chemical resistance as a Finish Coat to protect metal, concrete and wood surfaces in chemical plants, refineries, pulp and paper mills, waste and water treatment plants, electric generating stations, fertilizer plants, food processing, pharmaceutical, ore processing operations, marine installations, etc. ● Thin, 1 part, 1 coat floor coating with better abrasion resistance than epoxy.
<p>FEATURES</p>	<p>Excellent 'wetting out' properties over sound, rusty steel. Fast recoating, 1-2 hours. Forms a hard abrasive resistant surface. Can be applied at temperatures down to 40°F. Excellent corrosion resistance, passed 1,200 hours in salt cabinet. Very good weather resistance. High heat, up to 400°F dry. May be topcoated with most generic type coatings. Can be top coated with latex, enamel, polyurethane or epoxy.</p>
<p>PHYSICAL PROPERTIES</p>	<p>COLOR Aluminum FINISH Low sheen VOLUME SOLIDS 54% ± 2% COVERAGE 350-400 sq. ft. per gallon MIXING RATIO One component, stir well APPLICATION TEMPERATURE 18°F to 140°F dry APPLICATION METHOD Roller, brush or spray CURE TIME @ 75°F, 50% R.H. 1-2 hours, tack free; recoat 2-24 hours DRY SERVICE TEMP Up to 400°F V.O.C. 2.98 lbs/gal (356 gms/liter) SHELF LIFE Min. of 6 months in unopened containers stored at below 90°F POT LIFE 1-2 hours @ 75°F with 50% R.H. Will vary due to humidity</p>

Aluthane™ TECHNICAL DATA

SURFACE PREPARATION	<ol style="list-style-type: none"> Steel: For best results, sand blast to a SSPC-SP6 'commercial' blast finish. Where blasting is not appropriate, remove all loose rust and mill scale by power wire brushing or hand tool cleaning. A tightly adherent rusty surface is acceptable. Galvanized Steel: <u>New</u> - Brush blast per SSPC-SP7 or prime with Vinyl Wash Primer. <u>Old, Weathered, or Rusty</u> - Remove all oil, grease, dirt, and other foreign matter. Surface should be reasonably clean, dry, and free of contaminants. Remove all loose rust, etc., as outlined above under steel. Previously Painted Surfaces: Remove all loose, peeling, or blistered paint, and any other surface contaminants. Make sure surface is sound and dry.
MIXING INSTRUCTIONS	<p>Aluthane is made ready for use by stirring so that the aluminum pigment is thoroughly dispersed in the resin and a uniform 'silver' color is achieved. When used over a period of time, stir occasionally to maintain uniform mix. Thinning is not usually necessary. If needed, use up to 10% Urethane Reducer which is a water free grade.</p> <p>NOTE: Always wear protective gloves and clothing while mixing and applying Aluthane. Do not get on skin. Aluthane is difficult to remove.</p>
APPLICATION	<p>Aluthane may be applied by brush, roller, or spray. Roller cover should have a phenolic core and brushes should be natural bristles. For spray it is important that a moisture/oil trap be used on incoming air, and that fluid lines be flushed first with an anhydrous solvent (water free). Also, flush every 1-2 hours during use to keep lines clean from material build up. Required equipment is as follows:</p> <ol style="list-style-type: none"> Airless Spray - Use a minimum 20:1 ratio pump with 80-100 psi inbound air. Recommend a .013" - .017" tip. Adjust pressure for proper atomization based on selected tip. Convention spray - Use a dual regulated pot with 15 - 25 psi fluid pressure and 40-50 psi atomization pressure. A Binks #18 with a 704E tip/air cap is recommended. <p>When spraying, use a 50% overlapping crosshatch pattern to minimize the occurrence of pinholes. Do not apply to surfaces below 18°F or above 140°F. Do not apply over dew or frost. The surface should be dry and at least 5°F above the dew point.</p>
LIMITATIONS	<ol style="list-style-type: none"> Do not apply over frost, wet, or damp surfaces or extremely high humidity conditions. Partially used containers must be reclosed tightly to slow moisture in air from reacting with material and forming a tough skin. Skin can be removed and remaining material used. Be sure to stir. A gas 'blanket' injected into the can before resealing will slow/prevent air from reacting with the aluthane. Aluthane left on the lip of the can when resealing will make removal of the lid extremely difficult. It is best to use the entire contents of the aluthane container within a few days to avoid these problems. <p>Based on temperature of 75°F, Aluthane is tack free in 1-2 hours and may be overcoated in 2-4 hours. Always check for finger nail hardness. High temperatures and humidity will shorten recoat time.</p>
TRANSPORT	Regulated by USDOT, IATA & IMO. Flammable Liquid, UN 1493, Packing Group III, Class 8

SAFETY: This is a hazardous material if misused. Read and understand the Material Safety Data Sheet (MSDS) before use.

WARRANTY DISCLAIMER: The technical data given herein has been compiled for your help and guidance and is based upon our experience and knowledge. However, as we have no control over the use to which this information is put, no warranty, express or implied is intended or given except that these goods shall be of merchantable quality and buyer assumes all risk and liability for results obtained by the use of the materials covered in this data sheet, whether used singly or in combination with other products. We assume no responsibility whatsoever for coverage, performance or damages, including injuries resulting from use of this information or of products recommended herein. The sale and use of this product is governed by Progressive Products, Inc.'s Warranty Disclaimer and Return Policy.

Manufactured by:
GCPM in AL

Distributed by:
Progressive Epoxy Polymers, Inc.
48 Wildwood Dr.
Pittsfield, NH 03263-3406

Tel: 603-435-7199
Fax: 603-435-7182
www.epoxyproducts.com