

EPOXY CREAMTM TECHNICAL DATA

Two Part Epoxy Gel/Putty

**Smooth & Creamy Paste
Extended Potlife
Moisture Tolerant**

**Solvent-Free
VOC Class: Mastic VOC 0 g/l**

<p>STANDARD PRODUCT DESCRIPTION</p>	<p>Epoxy Cream is a 100% solids, low modulus, two component epoxy mastic for concrete, steel and wood surfaces. A trowelable adhesive or fairing compound formulated to patch or resurface horizontal, vertical or overhead surfaces. Epoxy Cream is a unique formulated moisture insensitive epoxy patching material that can cure in the presence of water.</p>
<p>FEATURES</p>	<p>May be applied to up 2" thick when patching holes Excellent chemical, abrasion and impact resistance Convenient 2:1 mix ratio Easily applied with trowel, putty knife or spatula Conforms to ASTM C-881, Type III, Grade 3, Glass B & C; AASHTO-M235-86 Used for leveling base plates and embedding bolts Non Toxic when cured After cure may be sanded, nailed, ground or drilled without cracking Moisture insensitive before, during and after cure Flows smoothly off putty knife/spatula</p>
<p>PHYSICAL PROPERTIES</p>	<p>COLOR Cloudy/semi clear COMPRESSIVE STRENGTH 10,000 psi ASTM-D695 MIXING RATIO 2:1 by volume THINNING Do not thin HARDNESS (SHORE D) 80 POT LIFE Up to 3.5 hours TENSILE STRENGTH 2,600 psi ASTM-D-638 V.O.C. 0 gms/l VOLUME SOLIDS 100% WATER ABSORPTION (24 hr ASTM-D-570) .5% MAXIMUM DRY SERVICE TEMP 150°F APPLICATION TEMP 50°F - 100°F THEORETICAL COVERAGE 1/5 Gal kit (neat) 9.6 sq. ft. @ 1/4" RECOMMENDED THICKNESS 1/8" - 1/2" SHELF LIFE 12 months minimum</p>

EPOXY CREAMTM TECHNICAL DATA

SURFACE PREPARATION	Surface to be coated should be free of oils, grease, loose debris and other contaminants.
APPLICATION	Epoxy Cream is prepared by mixing 2 parts base to 1 part curing agent. Do not vary from mix ratio proportions. Once mixed it can be used immediately, there is no induction time.
CAUTIONS	This product is sold without warranty as to performance expressed or implied. Users are urged to make their own tests to determine the suitability for their particular conditions. READ MSDS before use. KEEP AWAY FROM CHILDREN. For Industrial use only.
TRANSPORT	Epoxy base - Nonregulated by USDOT, IATA & IMO. Curing agent - USDOT, IATA & IMO 'Regulated' - Class 8, Packing group III, UN2735, Combustible Liquid IIIB. Curing agent quantities of under 4 liters is ORM-D exempt for ground shipment.

SAFETY: This is a hazardous material if misused. Read and understand the Material Safety Data Sheet (MSDS) before use.

WARRANTY DISCLAIMER: The technical data given herein has been compiled for your help and guidance and is based upon our experience and knowledge. However, as we have no control over the use to which this information is put, no warranty, express or implied is intended or given except that these goods shall be of merchantable quality and buyer assumes all risk and liability for results obtained by the use of the materials covered in this data sheet, whether used singly or in combination with other products. We assume no responsibility whatsoever for coverage, performance or damages, including injuries resulting from use of this information or of products recommended herein. The sale and use of this product is governed by Progressive Products, Inc.'s Warranty Disclaimer and Return Policy.

Manufactured by:
GCPM in AI

Distributed by:
Progressive Epoxy Polymers, Inc.
48 Wildwood Dr.
Pittsfield, NH 03263-3406

Tel: 603-435-7199
Fax: 603-435-7182
www.epoxyproducts.com
info@epoxyproducts.com